





Dear Customer,
the following instructions will help you realize a
beautiful and durable Bolon Woven Design Flooring.

Index

4 GENERAL CHECKING & PREPARATION OF THE SUBFLOORS

- 5 CONTAMINANTS
- 5 CRACKS
- 5 INSUFFICIENT SURFACE STRENGTH
- 5 PRIMER
- 6 UNDERFLOOR HEATING
- 6 SURFACE IRREGULARITIES
- 6 CLIMATIC CONDITIONS
- 7 MOIST SURFACES

8 INSTALLATION METHODS & INSTRUCTIONS

10 STEP-BY-STEP PROCEDURE

15 GUARANTEE

16 MISCELLANEOUS

A modern interior scene featuring a red velvet chair and a glass table with a cracked pattern. The chair is positioned in the center-left, with its backrest and seat visible. The table is on the left, showing a detailed, cracked, and textured surface. The background is a light-colored, textured wall. The text "OK FRIENDS, LET'S DO THIS!" is written in white, bold, sans-serif capital letters on the right side of the image.

OK FRIENDS,
LET'S DO THIS!



General checking and preparation of the subfloors

Before starting work, it is essential to check the subfloors. In general, the subfloors should be checked according to country-specific standards or regulations, which may include the following assessment criteria:

- Are the subfloors contaminated, for example by oil, wax, lacquer or paint residues?
- Are there cracks in the subfloors?
- Are the subfloors sufficiently firm, form-retaining and pressure-resistant?
- Are the subfloors dry enough?
- Are the surfaces of the subfloors porous or rough?
- Are any areas very uneven?
- Are the heights of the subfloors correct in relation to the adjacent building elements?
- Is there a heating protocol available?
- Are there suitable climatic conditions, i.e., temperature of the subfloors and rooms and room humidity?

If defects are discovered during the inspection of the subfloors, these must be reported to the client in writing.



INSUFFICIENT SURFACE STRENGTH

Sufficient surface strength is a very important condition for the long-term functionality of installed Bolon flooring. The surface of the substrate must form a solid construction together with the other building elements. This is tested with the so-called “scratch test” or by means of tensile tests (adhesive tensile strength measurement). If, following the measurement, the value of the tensile strength appears to be less than 1N/mm², it is necessary to reinforce the surface. In the case of a new screed, insufficient surface strength may be caused by insufficient binder (cement or gypsum) in relation to the gravel/sand used in construction. Measurement must always be performed by a trained professional who can provide the right recommendations for how to increase surface strength with primer and leveling compound.



CONTAMINANTS

Impurities (e.g., oil, wax, old adhesive or leveling compound residues, paint residues, etc.) must be removed from the subfloors because they reduce the adhesion of the materials to be applied, such as glue, primers and leveling compound. Under certain circumstances, this can cause the leveling layer to peel off. Prior to preparation and the installation of Bolon flooring, the floors must also be cleaned with an industrial vacuum to ensure they are dust-free.

CRACKS

Any cracks or false joints in the subfloor must be firmly sealed before installation begins. False joints are deliberately placed in the floor. Cracks are a form of damage and can have various causes. In both cases, the separated floor parts must be bonded back together to prevent them from moving independently of each other, which can lead to visible marks on the floor covering. Structural expansion joints must be respected and cannot be closed. It is therefore necessary that these joints are covered with a suitable profile.



PRIMER

Before laying Bolon flooring, a leveling compound must be applied. For this, the subfloors must always be sufficiently and evenly absorbent. The absorbency should be determined by a water drop test. By applying a primer that is adapted to the absorption capacity of the subfloor, the risk of pinholes and so-called elephant skin is reduced. The application of a primer is thus an absolute necessity, as it prevents the mixing water from being extracted from the leveling compound too quickly. Good substance binding improves the adhesion of the leveling compound to the subfloor.



UNDERFLOOR HEATING


Floor heating is increasingly being used in renovation projects. Slots are milled in the floor into which PVC pipes are then laid. These pipes usually lie about 2 mm below the surface of the screed. A uniform and solid surface is essential to the responsible and sustainable installation of Bolon flooring. The channels must be filled with special sealing compound intended for this purpose. After filling the channels a special primer should be used for ideal adhesion. Then level the layer to a thickness of approx. 3–5 mm. This ensures the floor is sufficiently flat, smooth and compressive for the installation of Bolon flooring. This layer thickness also ensures good heat distribution. Pipes must be laid so that the flooring material is not continuously exposed to temperatures higher than 30°C, as otherwise discoloration and other changes to the material can occur. Make sure the heating protocol is followed.

SURFACE IRREGULARITIES

Bolon floors should always be placed on completely level, smooth and flat subfloors in which there is no movement whatsoever. This prevents irregularities in the surface of the Bolon flooring. During leveling, a leveling compound is applied. To ensure maximum absorbency and self-levelling properties for bonding, a layer thickness of at least 2 mm is recommended, depending on the type of subfloor and type of leveling compound. The leveling must therefore take two properties into account: the best flow with the greatest possible absorption capacity.

CLIMATIC CONDITIONS

When installing Bolon flooring, adhesive and subfloors must be brought to the installation area at least 48 hours prior to installation. This gives these materials the chance to achieve a room temperature of 18°C–25°C. When Bolon flooring has been delivered in boxes placed on a pallet, be sure to remove the boxes from the pallet and spread them out in a single layer across a level surface. The relative air humidity must be 30–60 %. Higher levels of air humidity result in longer drying times and a risk of blistering. Due to the setting, drying and reaction times of the installation materials, the specified climatic conditions in the room must be observed before, during and up to 7 days after the completion of the floor covering work.



MOIST SURFACES

Before installation, check whether the surface is sufficiently dry. Excessive humidity in the subfloor is a common cause of damage. That is why measuring the moisture percentage is very important. A first indication is the period between the delivery of the subfloor (concrete or screed) and the moment at which the installation of the floor covering is started. The longer the period between the completion of the concrete or screed floor and the installation of the floor finish, the greater the chance that the subfloor has reached its equilibrium moisture content. Different subfloors have different drying times, depending on their composition.

The most used measurement method to determine the residual moisture in cement or calcium sulphate screeds is the CM measurement (calcium carbide method). In this method, a hole is tapped into the screed with a hammer and chisel. Be careful with heated constructions; the heating pipes must not be damaged. In the case of a screed with underfloor heating, the installer of the screed can mark the measurement point by means of a flag. No heating pipe may run within a radius of 10 cm around the marked point.

Thresholds CM measurement divided according to the amount of test material

Type Subfloor	Quantity of test material	Moisture percentage
Cement screed	50 g	<2,5% CM
Calcium sulphate bonded screed	100 g	<1,0% CM

Moisture measurements on concrete subfloors are usually determined using a moisture sensor according to the so-called hygrometric method. We normally assume that concrete with a relative humidity (RH) lower than 85% or lower than 2.5% CM value can be classified as ready for installation. If the RH is higher than 85% and/or higher than 2.5% CM value, solutions are available in the market to still continue the job. Always contact a technical advisor for the job in question as every project is different.



Installation methods and instructions

INSTALLATION METHODS ROLLS 200 CM

Installation methods	Bonding	Suitable applications	Recommendations by suppliers
Permanent	Adhesive: Use adhesive compatible for vinyl	On most prepared sub-floors with the exception of raised access floors	Uzin: KE2000S / KE66 Mapei: Ultrabond Eco 375 / 380 Thomsit: K188S / K188E Schönox: Durocoll / Protect F-Ball: F44 / F45 / F49

Please Note:

Although Bolon may suggest a selection of manufacturers of adhesive or non-adhesive products, we do not guarantee the products listed. The list of products and manufacturers are not guaranteed to be complete or current. Bolon will not accept any liability for the failure of any of these products to perform optimally with any Bolon products. It is the responsibility of the adhesive manufacturer and flooring contractor to ensure that the products used are appropriate for the application in question and applied in accordance with the manufacturer recommendations.



Step-by-step Procedure





Collections with no special cutting


1

Overlap 2 sheets of flooring by 4 cm.



2

Double cut.



Rolls with Bolon Green Weld

1


Cut the required lengths. Since the floor's appearance will change depending on lighting, direction of installation and the position of the viewer, consider incoming light and traffic to the area when installing the flooring. Avoid joints across the material. This is particularly important for striped or patterned articles where it is not possible for the stripes to be centered with each other across the entire width. The lengths must be laid in the same direction (see arrow on reverse).

2

The lengths are overlapped by approximately 4 cm and then double-cut to achieve a tight seam. For patterned articles, the overlap can have a specific dimension. **See pages 13 – 14**

3

Roll/fold the first sheet. Mark the position of the joint on the subfloor.




4

Roll/fold over the adjoining sheet and put masking tape on the sub-floor along the middle of the joint.



5

Glue the subfloor and remove the masking tape while still reachable.




6

Straighten out the first sheet.



7

Add Bolon Green Weld along the cross-section area of the sheet. Avoid overflow on floor covering surface.



8

Straighten out the adjoining sheet.



9

Gently soak up surplus Bolon Green Weld with a microfibre cloth.

10

Use a joint roller to ensure good contact between subfloor and floor covering.

11

Repeat steps 3-10 for the remaining sheets.

Collections with special cutting

BOLON BY YOU STRIPE


1

Overlap so the pattern is over two stripes are about 6 cm.



2

Cut so the stripe is around 3 cm.



BOLON BY YOU GRID

1

Overlap the entire smooth section over the mottled section.



2

Cut so that the smooth section is around 1.5 cm. The width of the mottled section is of secondary importance.



BOLON BY YOU DOT


1

Overlap 2 sheets of flooring by 4 cm.



2


Double cut. Avoid cutting in the big dots.



BOLON BY YOU GEOMETRIC

1

Overlap 2 sheets of flooring so the pattern repeat of two side-by-side squares is 15 cm.



2

Cut so one square is about 7.5 cm.




Collections with special cutting

GRAPHIC DUO

1

Overlap 2 sheets of flooring and adjust so that the repeated pattern is approx. 40 mm.



2

Double cut where the stripe is 20 mm.



GRAPHIC HERRINGBONE


1

Overlap 2 sheets of flooring and adjust so that the repeated pattern is approx. 180 mm.



2


Double cut where the stripe is 90 mm.



TRULY #1 ANYTHING EVERYTHING



1

Place the sheet with the green field on top and overlap the whole width of the field.



2

Cut so that 2 cm of the field is visible.




Guarantee

The installer should notify the manufacturer of any defective materials before proceeding with the installation. Within the scope of the product guarantees, the manufacturer is responsible for any defective materials. This refers to material defects identified prior to or during installation. Bolon cannot be held liable for poor workmanship or problems resulting from improper installation.

Miscellaneous

- After installation, the floor should be covered with suitable protection against dirt and damage.
- When skirting boards are used, we recommend installing them after the flooring.
- When Bolon flooring is installed on stairs, stair profiles and a permanent installation method must be used - no tackifier or tape.
- Wheels on office chairs must be polyamide (hard type, designed for textile flooring).
- Furniture feet must be made of Teflon, polythene, stainless steel, or a similar material.
- Some types of rubber used in trolley wheels, entrance mats, etc. can cause discoloration in the form of migration. This type of discoloration cannot be removed.
- Since Bolon flooring is a woven fabric with natural structural variations that cause light to reflect in different ways off the surface of the flooring, shades may appear to vary slightly.



If you need help with the installation of your Bolon flooring,
do not hesitate to contact us at sales.support@bolon.com